

Aperte

Marble

Marini
Dupré

By DYNAMIC STONE

5 Textures | 4 Sizes | 5/8" Thickness


16" x 32", 18" x 36"

24" x 24", 36" x 36"

Featured: Aperte

DCOF Testing	Results	Test	Results	Sizes
Century DCOF	0.68	Compression Breaking Load	810 kg/cm ²	16" x 32" x 5/8" Chevron Tile 4" x 12"
Elektron DCOF	0.67	Compression B.L. after Freezing Test	750 kg/cm ²	18" x 36" x 5/8" Plank 8" x FL
Leather DCOF	0.58	Bending Strength	119 kg/cm ²	24" x 24" x 5/8" Tile 4" x 16"
Micro DCOF	0.60	Volumetric Weight	2710 kg/m ³	36" x 36" x 3/4" Hexagon Tile 8"
Monet DCOF	0.50	Water Absorption	0.01%	Minimum order quantity - 500 sf
		Apparent Porosity	0.3%	
		Thermal Linear Expansion Coefficient	8.7 10 ⁶	
		Abrasion Test	2.2 mm	
		Impact Test	60 cm	
		Freeze-Defreeze Cycles	24 Cycles	Mosaics
		Microscopic Properties	Calcite - 99% Quartz - 1%	
				Random Interlocking Mosaic Stack 1" x 6" Hexagon 4"

Texture Options



Century Texture

Elektron Texture

Leather Texture

Micro Texture

Monet Texture

Symbols



Floor & Wall



Natural



Residential



Commercial